

TEXTURED		STUDDED		CHEQUER		EXCEL		SLATE	
SIZE 503 x 503mm		SIZE 503 x 503mm		SIZE 503 x 503mm		SIZE 503 x 503mm		SIZE 456 x 456mm	
THICKNESS EN438 - 4, 5, 7, & 9mm		THICKNESS EN438 - 5 & 7mm		THICKNESS EN438 - 4, 5 & 7mm		THICKNESS EN438 - 5 & 7mm		THICKNESS EN438 - 6mm	
WEIGHT 4mm - 6.4kg/m ² 5mm - 7kg/m ² 7mm - 9.21kg/m ² 9mm - 12.8kg/m ²		WEIGHT 5mm - 7kg/m ² 7mm - 9.21kg/m ²		WEIGHT 4mm - 6.4kg/m ² 5mm - 7kg/m ² 7mm - 9.21kg/m ²		WEIGHT 5mm - 7kg/m ² 7mm - 9.21kg/m ²		WEIGHT 6mm - 8kg/m ²	
Tiles Per Box	M² Per Box	Tiles Per Box	M² Per Box	Tiles Per Box	M² Per Box	Tiles Per Box	M² Per Box	Tiles Per Box	M² Per Box
4mm Qty 12	3m ²	5mm Qty 10	2.5m ²	4mm Qty 12	3m ²	5mm Qty 10	2.5m ²	6mm Qty 6	1.25m ²
5mm Qty 10	2.5m ²	7mm Qty 8	2m ²	5mm Qty 10	2.5m ²	7mm Qty 8	2m ²		
7mm Qty 8	2m ²			7mm Qty 8	2m ²				
9mm Qty 6	1.5m ²								

CLASSIFICATION

Norm / Product specification	-	EN ISO 10581
European Classification	EN ISO 10874	34/43
Fire Class	EN 13 501-1	Bfl-s1
Static Electrical Propensity	EN 1815	2 kV
Slip Resistance	EN 16165 app. B DIN 51130	R10

PERFORMANCE

Wear Resistance	EN 660.2	<2.0mm ³
Wear Group	-	T Group
Dimensional Stability	EN ISO 23999	≤0.25%
Dimensional Stability(average measured value)	-	≤0.10%
Residual indentation	EN ISO 24343-1	0.1mm
Castor Chair Test (type W)	ISO 4918	Ok
Colour Fastness	EN 20 105 - B02	Ok
Chemical Products Resistance	EN ISO 26987	Ok
Flexibility	ISO 24344 Method A	No Cracking
Shore Hardness	EN ISO 868	>40 H _D
Type Binder Content	ISO 10581	I Group
Thermal Conductivity	ISO 8302	0.25 W/(m.K)

ENVIRONMENTAL ACCREDITATIONS

TVOC after 28 days	ISO 16000-6	<100 µg/m ³
Certification	-	Floorscore®

CE MARKING



EN 14041

